



Carbae™ 105 and Carbae™ 108 are state-of-the-art carbon fiber packings that control your maintenance costs, without compromising performance. Carbae™ 105 is made from a 95% carbon assay, aerospace-grade fiber, coated with PTFE throughout. Carbae™ 108 uses the same fiber but is coated with a unique graphite dispersion.

Both Carbae™ 105 and Carbae™ 108 offer a low coefficient of friction and high thermal conductivity, so your process runs cooler and the packing lasts longer. For unparalleled economy and performance, choose the Carbae™ family of packing.



Specifications

105	108
Materials of Construction 95% carbon assay fiber; PTFE coating	95% carbon assay fiber; graphite dispersion
Temperature -328°F (-200°C) to +600°F (+316°C) atmosphere To +1200°F (+650°C) steam	-328°F (-200°C) to +850°F (+455°C) atmosphere To +1200°F (+650°C) steam
pH Range 0-14 (except strong oxidizers)	0-14 (except strong oxidizers)
Shaft Speed To 3,000 fpm (15 m/sec)	To 4,000 fpm (20 m/sec)
Pressure* To 500 psi (35 bar) Rotary/Centrifugal	To 500 psi (35 bar) Rotary/Centrifugal; To 2,500 psi (172 bar) Valves

*There are no known pressure limits that have been determined when Carbae™ 108 is combined as end ring material with die-formed GRAPH-LOCK™ center rings in valve installations.

Carbae™ 108 can be certified to contain less than 200 ppm leachable chlorides on request.

Value & Benefits

- Excellent cost/use ratio
- Ideal for most industrial equipment
- Compatible with a wide variety of chemicals
- Easy to install and remove

Ideal for

- Power generation
- Chemical/petrochemical
- Pulp & paper
- Primary metals
- General industrial use

Ordering Information

Size (Inches)	Standard Pkg/Min Order	Carbae 105		Carbae 108	
		Order Code	Yield ft/lb	Order Code	Yield ft/lb
1/8	1 lb. spool	40405-1008	74.1	40408-1008	125
	2 lb. spool	40405-1208		40408-1208	
	5 lb. spool	40405-2008		40408-2008	
3/16	1 lb. spool	40405-1012	31.9	40408-1012	55.6
	2 lb. spool	40405-1212		40408-1212	
	5 lb. spool	40405-2012		40408-2012	
1/4	2 lb. spool	40405-1216	23.3	40408-1216	29.0
	5 lb. spool	40405-2016		40408-2016	
5/16	2 lb. spool	40405-1220	15.9	40408-1220	19.8
	5 lb. spool	40405-2020		40408-2020	
3/8	5 lb. spool	40405-2024	11.5	40408-2024	13.8
	10 lb. spool	40405-3024		40408-3024	
7/16	5 lb. spool	40405-2028	8.3	40408-2028	10.1
	10 lb. spool	40405-3028		40408-3028	
1/2	5 lb. spool	40405-2032	6.5	40408-2032	8.4
	10 lb. spool	40405-3032		40408-3032	
9/16	5 lb. spool	40405-2036	5.4	40408-2036	6.9
	10 lb. spool	40405-3036		40408-3036	
5/8	5 lb. spool	40405-2040	4.4	40408-2040	5.5
	10 lb. spool	40405-3040		40408-3040	
3/4	5 lb. spool	40405-2048	3.3	40408-2048	3.8
	10 lb. spool	40405-3048		40408-3048	
7/8	10 lb. spool	40405-3056	2.3	40408-3056	2.9
1	10 lb. spool	40405-3064	1.6	40408-3064	2.5

AUTHORIZED DISTRIBUTOR



WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing.

While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues. Subject to change without notice.

GARLOCK is a registered trademark for packings, seals, gaskets, and other products of Garlock.

© Garlock Inc 2005. All rights reserved worldwide.

Garlock

Sealing Technologies®

www.garlock.com

Garlock Sealing Technologies
 1666 Division Street
 Palmyra, New York 14522 USA
 Phone: 1-315-597-4811
 Toll Free: 1-800-448-6688
 Fax: 1-315-597-3290
 Toll Free Fax: 1-800-543-0598

Other Garlock facilities are located in:

Columbia, SC, USA
 Phone 1.803.783.1880
 Fax 1.803.783.4279

São Paulo, Brazil
 Phone 55.11.4127.9935
 Fax 55.11.4343.5871

Saint-Étienne, France
 Phone 33.4.7743.5100
 Fax 33.4.7743.5151

Singapore
 Phone 65.6285.9322
 Fax 65.6284.5843

Houston, TX, USA
 Phone 1.281.459.7200
 Fax 1.281.458.0502

Sherbrooke, Canada
 Phone 1.819.563.8080
 Fax 1.819-563.5620

Neuss, Germany
 Phone 49.2131.3490
 Fax 49.2131.349.222

Shanghai
 Phone 86.021.62789702
 Fax 86.021.62787826

Sydney, Australia
 Phone 61.2.9793.2511
 Fax 61.2.9793.2544

W. Yorkshire, England
 Phone 44.1422.313600
 Fax 44.1422.313601

Mexico City, Mexico
 Phone 52.555.567.7011
 Fax 52.555.368.0418

Dubai, UAE
 Phone 971.4.8833652
 Fax 971.4.8833682